

Product Description & Application

Double-sided butyl mastic (synthetic rubber) with a paper interliner for use with all DuPont™ Tyvek® membranes. Suitable for nail sealing under battens, sealing laps, perimeters, chimneys, abutments and bonding roof membranes to eaves carrier. Particularly appropriate for branding DuPont™ Tyvek® membranes to masonry, brickwork, timber and metalwork and most plastic products.

Specifications

PROPERTY	VALUE
Stylename	1310B
Colour	black
Thickness	ca. 1,2 mm
Temperature range	from -30 °C to +90 °C (short exposure to higher temperature will not change properties)
Density	ca. 1,30 g/cm ³

Use and Care Recommendations

- Product is designed for the building industry. Tyvek® Butyl has a high immediate tack (adheres instantly to supports).
- Butyl is a plastic rubber and so it cannot be used for bonds, which are subjected to permanent mechanical stress.
- Users must check that the mastic is suitable for the support (adhesion, chemical compatibility, staining,...).
- The resistance to ageing, water, humidity and environmental cycling is excellent.
- The recommended application temperature is from +5 °C to +40 °C. The application should be done on a dry and clean surface (no dust, no grease, no solvent,...).
- Conditions: store rolls in their initial packaging, flat, in a clean and dry place. Storage temperature below +30 °C

Date: January 15, 2014

DuPont de Nemours
(Luxembourg) S.à r.l.
Rue General Patton,
L - 2984 Luxembourg
Tel.: +352 3666 5885
tyvek.info@lux.dupont.com

www.construction.tyvek.com

This information corresponds to our current knowledge on the subject. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.

